

Woven Vinyl Flooring Technical Data

TEST RESULTS

ISO-4892-2-Xenon Arc Lamp - Light Fades Rating 5 - Negligible/No Change

Outdoor/Indoor use

FVM SS/CUMSS 302 Flammability Approved – meets or exceeds

Non-flammable Federal Motor Vehicle Safety Std. No. 302 (NHTSA.DOT)

ASTM-D-5252 Hexapod Drum Test - Surface Appearance 4.5 Negligible/Slight Change

Durable

ASTM C-1028 Static Coefficient & Friction - Dry Average .81
ASTM C-1028 Static Coefficient & Friction - Wet Average .95

Safe from slippage

ASTM F-925 Std. Test Resistance to Chemical

Stain Resistant Rubbing Alcohol – No change

White Mineral Oil – No change Sodium hydroxide solution – No change

Hydrochloric acid solution – No change
Sulfuric acid solution – No change

Household ammonia solution – No change Household bleach solution – No change

Olive Oil – No change Kerosene – No change

White Vinegar – No change

Unleaded gasoline – No change

Phenol – No change

ASTM D7570 – Dimensional StabilityMachine Direction – Average +0.199%

Dimensionally stable Cross Direction – Average -0.115%

AATCC Test Method 129 Color Fastener to Ozone Rati

under high humidity. No. Cycles 8

Color fast to high heat and humidity conditions

Rating 5 - Negligible/No Change

Water Penetration Impact Test

No penetration occurred

10,000 cycles @ 10 lbs. per sq. in. Impervious to moisture penetration